

Product properties			Tolerance (EN 13489)	
Format	610 x 90 x 15 mm		Admissible difference in length	± 0.1 %
Packaging	Pack: 16 elements / 0.88 m² / 7.23 kg		Admissible difference in width	± 0.2 mm
	Pallet: 48 packs / 42.24 m² / 367.10 kg		Squareness of the element	≤ 0.2 %
Notes	- only suitable for all-over adhesion - cleaning and maintenance: see instruction guide - technical changes reserved		Longitudinal curvature along the element	≤ 0.1 %
			Transverse curvature across the width	≤ 0.2 %
			Height differences of elements	≤ 0.2 mm
			Moisture content at the time of first delivery (5-9%)	6 – 8%
Guarantee (acc. to Parador guarantee conditions)		25 years (private use) 10 years (commercial use)	Top layer	~ 3.5 mm

Product labelling



Classification general product features and surface characteristics

	Test method	Rating / Information
Profile		T & G
Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chair mat
Thermal resistance Suitable for installation over underfloor heating.	EN 12664	0.11 m ² *K/W
Formaldehyde (E1 = 0.1 ppm)	EN 16516	≤ 0.05 ppm
Slip resistance	EN 13893	μ ≥ 0.35
Reaction to fire	EN 13501-1	D _n s1
Chemical resistance	EN 13442	Category 5
Bond strength / Cross cutting test	ISO 2409	Category 1

Free sorting according to EN 13489

Type of wood (top layer):	Oak
Botanical name / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L., spp / QCXE
Internal abbreviation:	AFP CHEV-EI / N3 / 20221115
Grade:	Natur
Features (upper side of each plank) „Features shall be measured according to EN 1310“	
Sound sapwood	not allowed
Knot (intergrown)	allowed: up to 30mm
Open knots	allowed: up to 15mm
Pink knots	allowed: cluster of knots
Filling	allowed
Cracks / hairline cracks	allowed (no end cracks)
Bark pocket	not allowed
Lightning cracks	allowed
Slope of grain	allowed
Medullary ray	allowed
Discoloration, colour variation	allowed: uniform colours with slight differences
White streaks	not allowed
Pilling sticks marking	not allowed
Biodeterioration (EN 1311)	not allowed
Non-visible parts	
All the features without restrictions on size or length permitted provided they do not affect the strength or durability of the soil.	
Comment	
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.	